

Nominal Thickness (mm)	China GB 2521-96	Russia GOST 21427.1-83	Japan JS G2553-86	USA ASTM A876M-92	British		Germany DIN EN10107-96	France NF EN 10107-96
					BS 640418.7	BSEN 10107-96		
0.27	27QG100	3414	27HP100	-	-	M103-27P	M103-27P	M103-27P
	27QG110	3408	27HP110	27P146M	-	M103-27P	M103-27P	M103-27P
	27QG120	3407	27CG120	27H163M	-	-	-	-
	27QG130	3406	27CG130	27H163M	130-275	M130-275	M130-27S	M130-27S
	27QG140	3405	27CG140	-	089-27N5	M089-27N	M089-27N	M089-27N
0.3	30QG110	3408	30HP110	30P154M	-	M111-30P	M111-30P	M111-30P
	30QG120	3408	30HP120	30P154M	-	M117-30P	M117-30P	M117-30P
	30QG130	3405	-	30H183M	-	-	-	-
	30Q130	3406	30CG130	30H183M	-	-	-	NFC-28-920
								FEM140-30-3
	30Q140	3405	30CG140	30H183M	140-30S5	M140-30S	M140-30S	M140-30S
30Q150	3404	30CG150	-	097-30-N5	M098-30N	M097-30N	M097-30N	
0.35	35QG125	3408	35HP125	-	-	-	-	-
	35QG135	3407	35HP135	-	-	-	-	-
	35Q135	3407	-	-	-	-	-	-
	35Q145	3406	35CG145	-	-	M15035S	M150-35S	M150-35S
	35Q155	3405	35CG155	35H207M		M15035S	M150-35S	M150-35S
	35Q165	3404	35CG165	-	111-35-N5	M111-35N	M111-35N	M111-35N